

*RETURN TO FMF - LOCATION 7540

Pre Edit

QUERY CONTROL FORM		RTIS USE ONLY	
Application No. <u>10/030259</u>	Prepared by <u>BRS</u>	Tracking Number	
Examiner-GAU <u>Sheehan - 1742</u>	Date <u>5-6-04</u>	Week Date	
	No. of queries <u>1 CD</u>		

JACKET			
a. Serial No.	f. Foreign Priority	k. Print Claim(s)	p. PTO-1449
b. Applicant(s)	g. Disclaimer	l. Print Fig.	q. PTOL-85b
c. Continuing Data	h. Microfiche Appendix	m. Searched Column	r. Abstract
d. PCT	i. Title	n. PTO-270/328	s. Sheets/Figs
e. Domestic Priority	j. Claims Allowed	o. PTO-892	t. Other

SPECIFICATION	MESSAGE
a. Page Missing	<p><i>Claims/Punctuation: There is no punctuation at the end of claim 14. Please remedy.</i></p> <p><i>Thanks</i></p>
b. Text Continuity	
c. Holes through Data	
d. Other Missing Text	
e. Illegible Text	
f. Duplicate Text	
g. Brief Description	
h. Sequence Listing	
i. Appendix	
j. Amendments	
k. Other	
CLAIMS	
a. Claim(s) Missing	
b. Improper Dependency	
c. Duplicate Numbers	
d. Incorrect Numbering	
e. Index Disagrees	
f. Punctuation	
g. Amendments	
h. Bracketing	
i. Missing Text	
j. Duplicate Text	
k. Other	
	initials <u>BRS</u>
	RESPONSE
	<i>Corrected</i>
	initials <u>JBH</u>

Claim 12. (Currently Amended) The method ~~according to~~ of claim 1, characterized ~~in that~~ wherein during the hot-rolling step in the ~~ferrite~~ ferritic region, at least one deformation pass is carried out with the use of lubricant.

Claim 13. (Currently Amended) The method ~~according to~~ of claim 12, characterized ~~in that~~ wherein all deformation passes taking place in the ferritic region are carried out with roll lubrication.

Claim 14. (Currently Amended) The method ~~according to~~ of claim 1, characterized ~~in that~~ after cooling further comprising annealing the hot strip after the coiling step is annealed at an annealing temperature of at least 740 °C .

JBH
5-11-04

Claim 15. (Currently Amended) The method ~~according to~~ of claim 14, characterized ~~in that~~ further comprising annealing the coiled hot strip ~~is carried out~~ in a batch-type annealing furnace.

Claim 16. (Currently Amended) The method ~~according to~~ of claim 14, characterized ~~in that~~ wherein the annealing step is carried out in a continuous furnace.

Claim 17. (Currently Amended) The method ~~according to~~ of claim 1, characterized ~~in that~~ wherein the thickness of the coiled hot ~~coil~~ strip is ≤ 1.5 mm.